

Rec'd PCT/PTO 20 SEP 2005

REC'D 12 MAY 2004

WIPO

PCT

Pl 1166033

10/549950

THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME;

UNITED STATES DEPARTMENT OF COMMERCE
United States Patent and Trademark Office


May 07, 2004

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM
THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK
OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT
APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A
FILING DATE.

APPLICATION NUMBER: 60/456,528

FILING DATE: March 21, 2003

RELATED PCT APPLICATION NUMBER: PCT/US04/08369



By Authority of the
COMMISSIONER OF PATENTS AND TRADEMARKS

M. Tarver

M. TARVER
Certifying Officer

**PRIORITY
DOCUMENT**

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

BEST AVAILABLE COPY



03/21/03

PROVISIONAL APPLICATION FOR PATENT COVER SHEET

Approved for use through 10/31/2002. OMB 0851-0032
Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCETO: Box Provisional Application
Commissioner for Patents
United States Patent and Trademark Office
Washington, D.C. 20231J1050 U.S. PTO
60/456528

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53 (c).

Atty. Docket No. WSU 0200 PRV		
INVENTOR(s)		
FIRST NAME & MIDDLE INITIAL	LAST NAME	RESIDENCE (CITY & EITHER STATE OR FOREIGN COUNTRY)
Charles H.	Winter	Bloomfield Hills, Michigan
Charles L.	Dezelah, IV	Detroit, Michigan
Additional inventors are being named on the _____ separately numbered sheets attached hereto.		
TITLE OF THE INVENTION (500 characters max.)		
METAL OXIDE-CONTAINING NANOPARTICLES		
DIRECT ALL CORRESPONDENCE TO:		
 22045 PATENT & TRADEMARK OFFICE		
ENCLOSED APPLICATION PARTS (check all that apply)		
<input checked="" type="checkbox"/> Specification - Number of Pages <u>13</u> <input checked="" type="checkbox"/> Drawing(s) - Number of Sheets <u>5</u> <input type="checkbox"/> Application data sheet. See 37 CFR 1.76.		
CD(s). Number _____ Other: Specify _____		
METHOD OF PAYMENT OF FILING FEES (check one)		
<input checked="" type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. <input checked="" type="checkbox"/> A check or money order is enclosed to cover the Provisional Filing fees. <input type="checkbox"/> The Commissioner is hereby authorized to charge filing fees and credit Deposit Account Number: _____		PROVISIONAL FILING FEE AMOUNT(S) \$160.00 (large) \$ 80.00 (small) AMOUNT SUBMITTED OR TO BE CHARGED TO DEPOSIT ACCT. \$80.00

- ☒ Please charge any additional fee or credit any overpayment in connection with this filing to our Deposit Account No. 02-3978.
- ☒ The invention was not made by an agency of the United States Government or under a contract with an agency of the United States Government.
- ☐ The invention was made by an agency of the U.S. Government or under a contract with an agency of the U.S. Government. The name of the agency is _____, and the contract number is _____.
- ☒ A return postcard is enclosed.

Respectfully submitted,

SIGNATURE James Proscia
REGISTRATION NO. 47,010DATE March 21, 2003
TYPED OR PRINTED NAME James W. Proscia
TELEPHONE (248) 358-4400

CERTIFICATION UNDER 37 C.F.R. § 1.10

I hereby certify that this correspondence is being deposited with the United States Postal Service via Express Mail Label No. EV 212246545 US in an envelope addressed to: Box Provisional Patent Application, Commissioner for Patents, United States Patent and Trademark Office, Washington, D.C. 20231 onMarch 21, 2003
(Date of Deposit)Denise Sinnhuber
(Name of Person Signing)Denise Sinnhuber
(Signature)

METAL OXIDE-CONTAINING NANOPARTICLES

BACKGROUND OF THE INVENTION

1. Field of the Invention

5 The present invention is related to metal oxide-containing nanoparticles and to methods of making said metal oxide-containing nanoparticles; and in particular to copper oxide-containing nanoparticles that are reducible to copper metal by heating or by contacting with a reducing agent.

2. Background Art

10 Semiconductor technology increasingly requires the fabrication of faster and more densely packed integrated circuits. This increasing demand necessitates better control of conductive interconnects. Of particular interest is the formation of interconnects in trenches with high aspect ratios. It is anticipated that aspect ratios of 1.9 or higher will be required within the next decade. Currently, the most common methods of forming interconnects are by physical vapor
15 deposition, chemical vapor deposition, or electrochemical deposition. Aluminum and copper are the most common metals used for this purpose. In the typical application, trenches and other structures are overfilled with copper. Wafers treated in such a manner are then subjected to chemical mechanical polishing which is somewhat tedious and causes the surface of the interconnect to be curved.
20 Moreover, each of these techniques is somewhat susceptible to defects. More importantly, the vacuum coating technologies such as physical vapor deposition and chemical vapor deposition require significant capital equipment costs and are not able to achieve very high aspect ratios.

25 Metal nanoparticles have been recognized as potentially useful in forming conductive interconnects in such semiconductor devices. The nanoparticle size range is typically taken to be from about 1 nm to about 100 nm. Particles of

such dimensions exhibit unusual properties which may advantageously be applied when forming interconnects. Although such nanoparticles exhibit some collective atomic behavior, surface and quantum effects may be important. The lower melting points of nanosized metal particles make such particles attractive for interconnect technology. Such reduction in melting point can be over 500 °C with melting points of less than 350 °C attainable for many nanosized metals. In the typical application, a dispersed solution containing the nanoparticles is applied to a substrate having trenches by spin coating or some other dispersal technique. The nanoparticles will preferentially aggregate in the trenches. The substrate is then heated to sinter and/or melt the nanoparticles together thereby forming the interconnect.

U.S. Patent Application No. 20030008145 discloses a method of making metal nanocrystals that include passivating ligands. The metal nanoparticles of this application have enhanced solubility and/or dispersion because of the passivating ligands associated with the nanocrystals. However, metal containing nanoparticles are somewhat undesirable because of the increased reactivity of such particles and in particular to the potentially violent oxidation reaction that may occur in the presence of oxygen, water, or certain organic compounds.

Accordingly, there exists a need in the prior art for improved methods of making metal interconnects and for precursors for making such interconnects that are both economical and stable.

SUMMARY OF THE INVENTION

The present invention overcomes the problems of the prior art by providing a metal oxide-containing composition that includes nanoparticles described on average by Formula I:

$$M_xO_y \quad I \quad ; \text{ and}$$

one or more heteroatom donor ligands bonded to the surface of the nanoparticles,

where M is a metal; O is oxygen; and x and y are numbers having a ratio that is equal to the ratio of the average number of M atoms to the average number of O atoms in the nanoparticles. Typically, x and y will be reduced to simpler ratios by methods known to those skilled in the art. The nanoparticles are stabilized by the one or more heteroatom donor ligands which act as a protective layer that cap the surface of the nanoparticles. This allows for long-term stability and allows the nanoparticles to be readily modified to adjust solubility in a wide range of solvents. Moreover, the nanoparticles may be prepared having a variety of metal to oxygen ratios. The metal oxide-containing nanoparticles of the present invention typically have a narrow size distribution having mean sizes in the range of 1nm to 100nm in diameter.

In another embodiment of the present invention, a metal oxide nanoparticle-containing solution which takes advantage of the adjustability of the solubility of the metal oxide-containing nanoparticles is provided. The metal oxide-containing solution of the invention comprises the metal oxide composition set forth above and a solvent in which the metal oxide-containing nanoparticles are soluble.

In yet another embodiment of the present invention, a method for making metal oxide-containing nanoparticles is provided. The method of the invention comprises reacting solution of a metal ion solution with a heteroatom donor ligand to form a metal complex. The complex is next reacted with a reducing agent to form the metal oxide-containing nanoparticles. In a refinement of this embodiment, the metal oxide-containing nanoparticles are advantageously reduced to bulk metal upon heating at modest temperatures under an inert atmosphere. The temperature of reduction is believed to vary as a function of nanoparticle diameter. Thermal reduction of bulk copper oxides to copper has not been observed at temperatures less than 800 °C. Accordingly, such copper oxide-containing nanoparticles have potential application as precursors to high purity, low resistivity copper films and may serve as a means of filling sub-micron features on silicon wafers.

BRIEF DESCRIPTION OF THE DRAWINGS

FIGURE 1 is a transmission electron micrograph ("TEM") of pyridine-protected Cu_2O nanoparticles of the present invention.

5 FIGURE 2 are the plots of simultaneously performed differential thermal analysis and thermogravimetric analysis of the Cu_2O nanoparticles of the present invention.

FIGURE 3 is a plot of the thermogravimetric analysis and its derivative curve for the Cu_2O nanoparticles of the present invention.

10 FIGURE 4 is the powder X-ray diffraction ("XRD") of the Cu_2O nanoparticles of the present invention after heating to 800 °C under inert atmosphere.

FIGURE 5 is the XRD of the Cu_2O nanoparticles of the present invention after heating to 300 °C under inert atmosphere.

15 FIGURE 6 is the XRD of the Cu_2O nanoparticles of the present invention after heating to 400 °C under inert atmosphere.

FIGURE 7 are the plots of simultaneously performed differential thermal analysis and thermogravimetric analysis of unbound 2,2'-bipyridine.

20 FIGURE 8 are the plots of simultaneously performed differential thermal analysis and thermogravimetric analysis of copper(II) complex of 2,2'-bipyridine.

FIGURE 9 are the plots of simultaneously performed differential thermal analysis and thermogravimetric analysis of bulk Cu_2O .

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT(S)

Reference will now be made in detail to presently preferred compositions or embodiments and methods of the invention, which constitute the best modes of practicing the invention presently known to the inventors.

5 In an embodiment of the present invention, a metal oxide-containing composition is provided. The composition of the present invention comprises nanoparticles described on average by Formula I:



10 one or more heteroatom donor ligands bonded to the surface of the nanoparticles, wherein

M is a metal;

O is oxygen; and

x and y are numbers having a ratio that is equal to the ratio of the average number of M atoms to the average number of O atoms in the nanoparticles.

15 Preferably, M is a metal selected from beryllium, magnesium, aluminum, scandium, titanium, vanadium, chromium, manganese, iron, cobalt, nickel, copper, zinc, gallium, germanium, yttrium, zirconium, niobium, molybdenum, technetium, ruthenium, rhodium, palladium, silver, cadmium, indium, tin, antimony, lanthanum, cerium, praseodymium, neodymium, promethium, samarium, europium,

20 gadolinium, terbium, dysprosium, holmium, erbium, thulium, ytterbium, lutetium, hafnium, tantalum, tungsten, rhenium, osmium, iridium, platinum, gold, thallium, lead, bismuth, polonium, thorium, protactinium, uranium, neptunium, and plutonium. More preferably M is a metal selected from Group 9 through Group 11 elements; and most preferably, M is copper with the metal oxide nanoparticles

25 having formula II:



The average number of metal atoms and oxygen atoms in the nanoparticles is calculated from the range of possible mean diameters of the nanoparticles which is from about 1 nm to about 1000 nm. More preferably, the range of possible mean diameters is from about 1 nm to about 100 nm; and most preferably the mean diameters of the nanoparticles is less than about 20 nm. Preferably, the number of metal atoms M is from about 10 to about 5×10^{10} . More preferably, the number of metal atoms M is from about 10 to about 5×10^9 ; and most preferably the number of metal atoms M is less than about 4.0×10^5 atoms. The number of O atoms is preferably equal to at least about 0.01 times the number of M atoms. More preferably, the number of O atoms is equal to at least about 0.1 times the number of M atoms; and most preferably, the number of O atoms is equal to at least about 0.3 times the number of M atoms. Similarly, y is preferably equal to at least 0.01 x . More preferably y is equal to at least 0.1 x ; and most preferably, y is equal to at least 0.3 x . Typically, x and y will be reduced to simpler ratios by methods known to those skilled in the art. The maximum value for y is about that amount necessary to satisfy the valence of the highest oxidation state of the metal. However, slightly more oxygen may be present because of oxygen-based defects in the nanoparticles. Preferably, y is equal to or less than 5 x . More preferably y is equal to or less than about 3 x . For example, for a nanoparticle of 200 M atoms and 100 O atoms the formula will be expressed as M_2O . The nanoparticles of the present invention may be crystalline (nanocrystals) or may be amorphous. The typical nanoparticles are spherical particles, but other shapes may be suitable. Metal oxide-containing nanoparticles of the following morphologies are of potential interest: spherical, ellipsoidal, rod-shaped, polyhedral, as well as others.

The metal atoms of the nanoparticles may be of uniform oxidation state or may be present as mixtures of oxidation states. Different oxidation states of the metal are one or more of the values selected from 0, +1, +2, +3, +4, +5, +6, +7, and +8. In the case of copper, the most likely copper oxidation states are 0, +1, and +2, but others are possible. The typical copper oxide nanoparticle preparation (as given in synthesis description below) results in particles that are uniformly composed of cuprite, Cu_2O .

The nanoparticles are protected from oxidation and/or agglomeration by virtue of a protective (or passivating) layer by the one or more heteroatom donor ligands that are chemically bonded to the surfaces of the nanoparticles. The nature of the protective ligand allows for the nanoparticles to be dissolved or finely dispersed in a variety of liquid solvents. The protective ligands can easily be tailored by adding or changing functional groups such that a high degree of solubility is achieved in the solvent of choice. For example, by using 2,2'-bipyridine as the protective ligand copper oxide particles can be prepared that are soluble in methanol, ethanol, 1-propanol, isopropanol, 1-butanol, acetone, dichloromethane, ethylene glycol, as well as other polar solvents. By using 2,2'-bipyridine to which long alkyl chains have attached to the aromatic ring, solubility in non-polar solvents has been achieved. Another example is where the protective ligand is derived from decanoic acid whereby the copper oxide nanoparticles are soluble in non-polar solvents such as hexane. By such a strategy it is envisioned that particles could be made to exhibit solubility in solvents ranging from polar, hydrogen-bonding solvents to non-polar hydrocarbon species and their perfluorinated derivatives, including hexanes and perfluoromethylcyclohexane.

Protecting ligands include all compounds containing an oxygen or nitrogen atom that is capable of acting as an electron-pair donor to form a bond to the nanoparticle surface. Nitrogen donor examples include, but are not limited to, alkyl amines, pyridine, 2,2'-bipyridine, pyrrole, pyrazole, imidazole, triazole, tetrazole, nitriles, and any substituted variations and salts thereof. Oxygen donor examples include, but are not limited to, carboxylic acids, carbonates, nitrates, nitroalkanes, nitroarenes, hydroxamic acids, ketones, aldehydes, esters, and any substituted variations and salts thereof. Furthermore, it is anticipated that some of the most useful protecting ligands will have some degree of charge stabilization. The nature of ligands having such capability can be described as follows: a) nanoparticle surface is capped by a ligand as described above which bears a charge; the charge may be localized on one or more of the donor-atoms, or localized on one or more of the non-donor atoms, or it may be delocalized through a number of donor and/or non-donor atoms, b) associated with the charge bearing ligands are some number of oppositely charged species which may provide additional stabilization arising from

some combination of steric bulk and the formation of a charge barrier. In addition to the one or more heteroatom donor ligands, the metal oxide-containing composition of the present invention may further include one or more loosely bound heteroatom ligands. As used herein, loosely bound means that the heteroatom
5 ligands are associated with the nanoparticles, but are not bonded to the nanoparticles as the one or more heteroatom donor ligands. Such an association may be by electrostatic interaction. Examples of such ligands include, for example, a heteroatom donor ligand (in this instance the heteroatom donor ligand is not as strongly bonded to the surface of the nanoparticles as described above), nitrate,
10 halide, phosphate, perchlorate, formate, acetate, borate, hydroxide, silicate, carbonate, sulfite, sulfate, nitrite, phosphite, water, or mixtures thereof.

The thermal behavior of the metal oxide nanoparticles is of central interest to the present invention, particularly the observed reduction of the metal oxide-containing nanoparticles to bulk metal upon mild heating. The individual
15 thermal events for a typical sample of metal oxide nanoparticles are as follows: loss of unbound and/or loosely bound ligand, loss of bound ligand, and reduction of metal oxide nanocrystals to bulk metal. The loss of unbound and loosely bound ligand is expected to occur at temperatures at or near the boiling point or sublimation temperature of the ligand molecule. This would generally occur over a
20 narrow temperature range, somewhere between 50 °C and 250 °C, depending on the ligand and metal. The loss of bound ligand will generally occur at a temperature significantly higher than that of the unbound ligand; a certain amount of additional energy is required to break bonds to the surface of the nanoparticle. Loss of bound ligand would generally occur at between 100 °C and 300 °C and may be
25 accompanied by ligand decomposition. Reduction of copper oxide-containing nanoparticles to copper generally occurs between 300 °C and 500 °C, with lower reduction temperatures being preferred. The typical preparation (as given below) results in Cu₂O nanoparticles having diameters estimated near 4 nm that reduce to bulk copper at around 380 °C. Bulk phase Cu₂O is not reduced upon heating, even
30 with temperatures as high as 800 °C. The observed low-temperature thermal reduction represents a potentially novel, nano-phase phenomenon that is not known for the bulk-phase of this material. This property, being a result of the size regime

of the material, is strongly believed to behave as a function of particle size; the reduction temperature should vary with nanoparticle diameter as a consequence.

5 In another embodiment of the present invention, a metal oxide-containing solution which takes advantage of the adjustability of the solubility of the metal oxide-containing nanoparticles is provided. The metal oxide-containing solution of the invention comprises the metal oxide composition set forth above and a solvent in which the metal oxide-containing nanoparticles are soluble. As set forth above, the solubility of the metal oxide-containing nanoparticles is adjustable by appropriate selection of the one or more heteroatom donor ligands. This metal oxide-containing solution is particularly useful in applying the nanoparticles to a substrate. Specifically, a substrate is contacted with a nanoparticle-containing solution and then the solvent is evaporated or allowed to evaporate leaving behind the nanoparticles. The metal oxide nanoparticles are then optionally converted to zero-valent metal by heating. In the case of copper oxide-containing nanoparticles 10 with a mean diameter of about 4 nm, this conversion occurs at a temperature of at least 100 °C. Alternatively, the conversion to zero-valent metal is accomplished by contacting the metal oxide-containing nanoparticles with a reducing agent. Suitable reducing agent, include but are not limited to, molecular hydrogen, alcohols, amines, or mixtures thereof.

20 In yet another embodiment of the present invention, a method for making metal oxide-containing nanoparticles is provided. The method of the invention comprises reacting a metal ion in solution (i.e., from a salt) with a heteroatom donor ligand to form a metal complex. Preferably the mole ratio of metal ion to ligand is from about 0.05 to about 20. More preferably, the mole ratio of metal ion to ligand is from about 2 to 6. The metal complex is next reacted with a reducing agent to form the metal oxide-containing nanoparticles. For example, to make copper oxide-containing nanoparticles, CuX_2 is reacted with a heteroatom donor ligand to form a copper complex. Preferably the mole ratio of CuX_2 to ligand is from about 0.05 to about 20. More preferably, the mole ratio of CuX_2 to ligand 25 is from about 0.5 to 10; most preferably the mole ratio of CuX_2 to ligand is from about 2 to 6. The copper complex is next reacted with a reducing agent to form the

5 copper oxide-containing nanoparticles. Suitable reducing agents include, but are not limited to, sodium borohydride, lithium aluminum hydride, molecular hydrogen, sodium metal, zinc metal, magnesium metal, aluminum metal, hydrazine, and the like. X is a metal ion counterion. Suitable examples for X include, but are not limited to, halide, nitrate, phosphate, perchlorate, formate, acetate, borate, hydroxide, silicate, carbonate, sulfite, sulfate, nitrite, phosphite, hydrates thereof; and mixtures thereof. The properties of the metal oxide-containing nanoparticles, preferred and suitable metals M, and suitable heteroatom donor ligands are the same as those set forth above for the metal oxide-containing composition set forth above.

10 The method of the present invention also optionally includes the step of reacting the metal oxide-containing nanoparticles at a sufficiently high temperature to form metal. In the case of copper oxide-containing nanoparticles, the copper oxide-containing nanoparticles are heated to a temperature of at least 100 °C. Alternatively, the conversion to metal is accomplished by contacting the metal
15 oxide nanoparticles with a second reducing agent. Suitable second reducing agents, include but are not limited to, molecular hydrogen, alcohols, amines, or mixtures thereof.

The following examples illustrate the various embodiments of the present invention. Those skilled in the art will recognize many variations that are
20 within the spirit of the present invention and scope of the claims.

SYNTHESIS OF COPPER OXIDE NANOPARTICLES

Described herein is a typical synthesis of copper oxide nanoparticles as described by Scheme I. The particles obtained consist of Cu_2O , estimated to be about 4 nm in size, having a 2,2'-bipyridine ("bipy") protective ligand coat. The
25 synthesis is readily scalable, typically giving high yields (>80%, >2g) of a free-flowing reddish-brown powder. The product is soluble in polar organic solvents such as methanol, ethanol, acetone, and dichloromethane, as well as others. The solid form of the sample can be readily achieved from solutions by removal of solvent under reduced pressure. As a solid, the sample is stable indefinitely if stored

at room temperature under argon. The solution is stable for at least one month in an oxygen and moisture free environment. Upon long-term exposure to air, the solid sample retains its properties for at least one week. The sample in solution typically begins to show signs of decomposition after few hours of exposure to air.

5

1. Synthetic Example

Aqueous copper(II) nitrate (0.167 M, 150 mL) was treated with 2,2'-bipyridine (3.905 g, 0.025 mol) under rapid stirring. Aqueous sodium borohydride (5.0 mM, 80 mL) was added dropwise to the rapidly stirring solution, which had been cooled to 0 °C. Upon reduction the reaction mixture became dark reddish-brown in color. As a brown precipitate began to form, the vigorous effervescence of the reaction mixture led to foaming. Stirring was continued, making occasional adjustments so as to accommodate foaming. Upon cessation of foaming and effervescence a dark brown solid was isolated by vacuum filtration. The soluble material was then extracted by treating the solid with several portions of absolute ethanol until the filtrate was colorless. The filtrate was taken to dryness and washed with 20 mL of tetrahydrofuran ("THF") to remove excess ligand. Using standard Schlenk techniques under inert atmosphere, soluble nanoparticles were extracted from the residue using three 40 mL portions of CH₂Cl₂. The solution was taken to dryness under vacuum to afford a rust-colored powder that could be readily redissolved in polar organic solvents.

2. Characterization of Copper Oxide-Containing Nanoparticles

A number of methods of characterization have been used to study the copper oxide-containing nanoparticles. Proton Nuclear Magnetic Resonance (1H NMR) of the sample revealed signals that are consistent with the protons of the protecting ligand (in the above case 2,2'-bipyridine). Infrared absorption spectroscopy (IR) for the sample is also consistent with the presence of the protecting ligand (in the above case 2,2'-bipyridine), but also shows peaks that suggest the presence of nitrate, which may be present also as a bound ligand.

Powder X-ray diffraction (XRD) data for the sample is inconclusive and may indicate that the particles are amorphous or are very small nanoparticles.

Transmission electron microscopy images have been collected for a copper oxide-containing nanoparticle sample where the ligand is 2,2'-bipyridine and for the analogous pyridine-capped nanoparticle sample. The micrographs from the 2,2'-bipyridine protected sample were consistent with particles of a size on the order of 4 nm. The micrographs of the pyridine-capped copper oxide-containing particles convincingly display relatively monodisperse particles of a mean size near 5.5 nm (Figure 1). The transmission electron micrograph for these nanoparticles prepared displays both spherical and near-spherical particles having a mean diameter of 5.46 nm. The standard deviation in particle diameter is 1.18 nm (~20% the mean diameter), indicative of a reasonably narrow distribution of size. A number of the particles exhibit distinct lattice fringes, as would be expected for nanocrystals. For other particles the lattice fringes are indistinct or absent. Particles lacking lattice fringes may either be amorphous, lacking a well-defined lattice, or may be crystalline, but positioned in such a way that the lattice is not readily observed. The transmission electron micrograph for cuprite nanoparticles prepared with 2,2'-bipyridine as the capping ligand also displays spherical and near-spherical particles. The mean diameter of the particles is 3.82 nm, with a standard deviation of 0.81 nm. Again, the particles exhibit a reasonably narrow size distribution, with the standard deviation being ~20% of the mean diameter. Lattice fringes are observed for a number of the particles.

Differential thermal analysis (DTA) and thermogravimetric analysis (TGA) were performed simultaneously on a solid sample of 2,2'-bipyridine protected copper oxide-containing nanoparticles (Figures 2 and 3). Four regions of interest were found in the DTA of the sample: an endotherm at 201 °C, an exotherm at 262 °C, an endotherm at 301 °C, and an exotherm at 377 °C. The TGA exhibited two major regions of weight loss: a loss of 39% of the sample weight centered at 249 °C, and a loss of 8% centered at 374 °C. The DTA/TGA residue after heating to 800 °C in an inert atmosphere was determined to be bulk copper by XRD (Figure 4). Heating the sample to 300 °C under DTA/TGA conditions yielded material that

was identified by XRD as being predominantly Cu_2O , where the crystalline domain was small ($< 10\text{nm}$) as determined by line broadening (Figure 5). Upon heating to 400°C , the residue was observed to become bulk phase copper as determined by XRD (Figure 6).

5 To understand better the implications of the DTA/TGA data, DTA/TGA was performed on a series of reference materials. The endotherm at 201°C correspond well to that observed for the volatilization point of unbound 2,2'-bipyridine (Figure 7). The fact that this endotherm is not accompanied by a weight loss for the nanoparticle sample indicates that the amount of unbound (or
10 loosely bound) 2,2'-bipyridine in the sample is small. The exotherm at 262°C and the weight loss centered at 249°C appear to concur with the loss of bound 2,2'-bipyridine as determined by comparison to the DTA/TGA of the copper(II) complex of 2,2'-bipyridine (Figure 8). The exotherm at 377°C and the concurrent weight loss at 374°C are clearly due to the loss of oxygen from Cu_2O to give copper
15 as stated above. DTA/TGA was performed on a sample of bulk Cu_2O (Figure 9); no thermal features were observed. The residue was found to be bulk Cu_2O after heating to 800°C under inert atmosphere.

While embodiments of the invention have been illustrated and described, it is not intended that these embodiments illustrate and describe all
20 possible forms of the invention. Rather, the words used in the specification are words of description rather than limitation, and it is understood that various changes may be made without departing from the spirit and scope of the invention.

WHAT IS CLAIMED IS:

1 1. A metal oxide-containing composition, the composition
2 comprising:
3 metal oxide nanoparticles described on average by Formula I:
4 M_xO_y I ; and
5 one or more heteroatom donor ligands bonded to the surface of the
6 nanoparticles,
7 wherein
8 M is a metal;
9 O is oxygen; and
10 x and y are numbers having a ratio that is equal to the ratio of the
11 average number of M atoms to the average number of O atoms in the nanoparticles,
12 wherein the number of M atom is from about 10 to about 5×10^{10} atoms and the
13 number of O atoms is at least about 0.01 times the number of M atoms.

1 2. The metal oxide- containing composition of claim 1 wherein
2 M is a metal selected from beryllium, magnesium, aluminum, scandium, titanium,
3 vanadium, chromium, manganese, iron, cobalt, nickel, copper, zinc, gallium,
4 germanium, yttrium, zirconium, niobium, molybdenum, technetium, ruthenium,
5 rhodium, palladium, silver, cadmium, indium, tin, antimony, lanthanum, cerium,
6 praseodymium, neodymium, promethium, samarium, europium, gadolinium,
7 terbium, dysprosium, holmium, erbium, thulium, ytterbium, lutetium, hafnium,
8 tantalum, tungsten, rhenium, osmium, iridium, platinum, gold, thallium, lead,
9 bismuth, polonium, thorium, protactinium, uranium, neptunium, and plutonium.

1 3. The metal oxide- containing composition of claim 1 wherein
2 M is a metal selected from Group 9 through Group 11 elements.

1 4. The metal oxide- containing composition of claim 1 wherein
2 the one or more heteroatom donor ligands include compounds containing an oxygen
3 or nitrogen atom that are capable of acting as an electron-pair donor to form a bond
4 to the surface of the nanoparticles.

1 5. The metal oxide-containing composition of claim 1 wherein
2 the one or more heteroatom donor ligands are selected from the group consisting of
3 alkyl amines, pyridine, 2,2'-bipyridine, pyrrole, pyrazole, imidazole, triazole,
4 tetrazole, nitriles, carboxylic acids, carbonates, nitrates, nitroalkanes, nitroarenes,
5 hydroxamic acids, ketones, aldehydes, and esters.

1 6. The metal oxide- containing composition of claim 1 wherein
2 the nanoparticles have a mean diameter from about 1 nm to 1000 nm.

1 7. The metal oxide- containing composition of claim 1 wherein
2 the nanoparticles have a mean diameter from about 1 nm to 100 nm.

1 8. The metal oxide-containing composition of claim 1 wherein
2 the nanoparticles have a mean diameter less than about 20 nm.

1 9. The metal oxide-containing composition of claim 1 wherein
2 the nanoparticles have a spherical, ellipsoidal, rod-shaped, or polyhedral
3 morphology.

1 10. The metal oxide-containing composition of claim 1 wherein
2 the metal oxide nanoparticles include amorphous or crystalline domains.

1 11. The metal oxide-containing composition of claim 1 wherein
 the nanoparticles include a mixture of metal atoms in different oxidation states.

1 12. The metal oxide-containing composition of claim 10 wherein
2 the different oxidation states are one or more of the values selected from 0, +1,
3 +2, +3, +4, +5, +6, +7, and +8.

1 13. The metal oxide-containing composition of claim 1 further
2 comprising one or more loosely bound heteroatom ligands.

1 14. The metal oxide-containing composition of claim 13 wherein
2 the one or more loosely bound heteroatom ligands are nitrate, halide, phosphate,
3 perchlorate, formate, acetate, borate, hydroxide, silicate, carbonate, sulfite, sulfate,
4 nitrite, phosphite, water, alkyl amines, pyridine, 2,2'-bipyridine, pyrrole, pyrazole,
5 imidazole, triazole, tetrazole, nitriles, carboxylic acids, carbonates, nitrates,
6 nitroalkanes, nitroarenes, hydroxamic acids, ketones, aldehydes, esters or mixtures
7 thereof.

1 15. A metal oxide-containing solution, the solution comprising:
2 a solvent;
3 metal oxide nanoparticles described on average by Formula I:
4 M_xO_y I ; and
5 one or more heteroatom donor ligands bonded to the surface of the
6 nanoparticles,
7 wherein
8 M is a metal;
9 O is oxygen; and
10 x and y are numbers having a ratio that is equal to the ratio of the
11 average number of M atoms to the average number of O atoms in the nanoparticles,
12 wherein the number of M atom is from about 10 to about 5×10^{10} atoms and the
13 number of O atoms is at least about 0.01 times the number of M atoms.

1 16. The metal oxide-containing solution of claim 15 wherein the
2 heteroatom donor ligand is derived from decanoic acid and the solvent is hexane.

1 17. The metal oxide-containing solution of claim 15 wherein the
2 heteroatom donor ligand is 2,2'-bipyridine and the solvent is a polar solvent.

1 18. The metal oxide-containing solution of claim 15 wherein the
2 solvent comprises at least one compound selected from the group consisting of
3 methanol, ethanol, 1-propanol, isopropanol, 1-butanol, acetone, dichloromethane,
4 and ethylene glycol.

1 19. The metal oxide-containing solution of claim 15 wherein the
2 heteroatom donor ligand is 2,2'-bipyridine to which long chain alkyls have been
3 attached and the solvent is a nonpolar solvent.

1 20. A method of applying metal oxide-containing nanoparticles
2 to a substrate, the method comprising:

- 3 1) contacting the substrate with the solution of claim 15; and
4 2) evaporating the solvent or allowing the solvent to evaporate.

1 21. The method of claim 20 further comprising:

- 2 3) heating the metal oxide-containing nanoparticles at a
3 sufficiently high temperature to form zero-valent metal.

1 22. The method of claim 21 wherein the metal oxide nanoparticles
2 are heated to a temperature of at least 200 °C.

1 23. The method of claim 20 further comprising contacting the
2 metal oxide nanoparticles with a reducing agent.

1 24. The method of claim 23 wherein the reducing agent is selected
2 from the group consisting of molecular hydrogen, alcohols, amines, or mixtures
3 thereof.

1 25. A copper oxide-containing composition, the composition
2 comprising:

3 copper oxide nanoparticles described on average by Formula I:

4 Cu_xO_y II ; and

5 one or more heteroatom donor ligands bonded to the surface of the
6 nanoparticles,

7 wherein

8 Cu is copper;

9 O is oxygen; and

10 x and y are numbers having a ratio that is equal to the ratio of the
11 average number of Cu atoms to the average number of O atoms in the nanoparticles,
12 wherein the number of Cu atoms is from about 10 to about 5×10^{10} atoms and the
13 number of O atoms is at least about 0.01 times the number of Cu atoms.

1 26. The copper oxide- containing composition of claim 25 wherein
2 the one or more heteroatom donor ligands include compounds containing an oxygen
3 or nitrogen atom that is capable of acting as an electron-pair donor to form a bond
4 to the surface of the nanoparticles.

1 27. The copper oxide-containing composition of claim 25 wherein
2 the one or more heteroatom donor ligands are selected from the group consisting of
3 alkyl amines, pyridine, 2,2'-bipyridine, pyrrole, pyrazole, imidazole, triazole,
4 tetrazole, nitriles, carboxylic acids, carbonates, nitrates, nitroalkanes, nitroarenes,
5 hydroxamic acids, ketones, aldehydes, and esters.

1 28. The copper oxide- containing composition of claim 25 wherein
2 the nanoparticles have an mean diameter from about 1 nm to 1000 nm.

29. The copper oxide- containing composition of claim 25 wherein
the nanoparticles have an mean diameter from about 1 nm to 100 nm.

1 30. The copper oxide-containing composition of claim 25 wherein
2 the nanoparticles have an mean diameter less than about 20 nm.

1 31. The copper oxide-containing composition of claim 25 wherein
2 the nanoparticles have a spherical, ellipsoidal, rod-shaped, or polyhedral
3 morphology.

1 32. The copper oxide-containing composition of claim 25 wherein
2 the copper oxide nanoparticles are amorphous or crystalline.

1 33. The copper oxide-containing composition of claim 25 wherein
the nanoparticles include a mixture of copper atoms in different oxidation states.

1 34. The copper oxide-containing composition of claim 32 wherein
2 the different oxidation states are 0, +1, and +2.

1 35. The copper oxide-containing composition of claim 25 further
2 comprising one or more loosely bound heteroatom ligands.

1 36. The copper oxide-containing composition of claim 35 wherein
2 the one or more additional heteroatom containing molecules are nitrate, halide,
3 phosphate, perchlorate, formate, acetate, borate, hydroxide, silicate, carbonate,
4 sulfite, sulfate, nitrite, phosphite, water, alkyl amines, pyridine, 2,2'-bipyridine,
5 pyrrole, pyrazole, imidazole, triazole, tetrazole, nitriles, carboxylic acids,
6 carbonates, nitrates, nitroalkanes, nitroarenes, hydroxamic acids, ketones,
7 aldehydes, esters, or mixtures thereof.

1 37. A copper oxide-containing solution, the solution comprising:
2 copper oxide nanoparticles described on average by Formula I:
3 Cu_xO_y II ;
4 one or more heteroatom donor ligands bonded to the nanoparticles;
5 and
6 a solvent,
7 wherein
8 Cu is copper;
9 O is oxygen; and
10 x and y are numbers having a ratio that is equal to the ratio of the
11 average number of Cu atoms to the average number of O atoms in the nanoparticles,
12 wherein the number of Cu atoms is from about 10 to about 5×10^{10} atoms and the
13 number of O atoms is at least about 0.01 times the number of Cu atoms.

1 38. The copper oxide-containing solution of claim 37 wherein the
2 heteroatom donor ligand is derived from decanoic acid and the solvent is hexane.

1 39. The copper oxide-containing solution of claim 37 wherein the
2 heteroatom donor ligand is 2,2'-bipyridine and the solvent is a polar solvent.

1 40. The copper oxide-containing solution of claim 37 wherein the
2 solvent comprises a component selected from the group consisting of methanol,
3 ethanol, 1-propanol, isopropanol, 1-butanol, acetone, dichloromethane, and ethylene
4 glycol.

1 41. The copper oxide-containing solution of claim 37 wherein the
2 heteroatom donor ligand is 2,2'-bipyridine to which long chain alkyls have been
3 attached and the solvent is a nonpolar solvent.

4 42. A method for making metal oxide-containing nanoparticles,
5 the method comprising:
6 reacting a metal ion in solution with a heteroatom donor ligand to
7 form a metal complex; and
8 reducing the metal complex with a reducing agent to form the metal
9 oxide-containing nanoparticles.

1 43. The method of claim 42 wherein the metal ion solution is
2 formed by dissolving a metal salt in a solution.

1 44. The method of claim 42 wherein the mole ratio of metal ion
2 to ligand is from about 0.05 to about 20.

1 45. A method for making copper oxide-containing nanoparticles,
2 the method comprising:

3 1) reacting CuX_2 with a heteroatom donor ligand to form a
4 copper complex; and

5 2) reacting the copper complex with a first reducing agent to
6 form the copper oxide-containing nanoparticles, wherein X is a metal ion
7 counterion.

1 46. The method of claim 45 wherein X is selected from the group
2 consisting of halide, nitrate, phosphate, perchlorate, formate, acetate, borate,
3 hydroxide, silicate, carbonate, sulfite, sulfate, nitrite, phosphite, hydrates thereof;
4 and mixtures thereof.

1 47. The method of claim 45 wherein the one or more heteroatom
2 donor ligands include compounds containing an oxygen or nitrogen atom that is
3 capable of acting as an electron-pair donor to form a bond to the surface of the
4 nanoparticles.

1 48. The method of claim 45 wherein the one or more heteroatom
2 donor ligands are selected from the group consisting of alkyl amines, pyridine,
3 2,2'-bipyridine, pyrrole, pyrazole, imidazole, triazole, tetrazole, nitriles, carboxylic
4 acids, carbonates, nitrates, nitroalkanes, nitroarenes, hydroxamic acids, ketones,
5 aldehydes, and esters.

1 49. The method of claim 45 wherein the copper oxide-containing
2 nanoparticles include a mixture of copper atoms in different oxidation states.

1 50. The method of claim 49 wherein the different oxidation states
2 are 0, +1, and +2.

1 51. The method of claim 45 wherein the first reducing agent is
2 sodium borohydride, lithium aluminum hydride, molecular hydrogen, sodium
3 metal, zinc metal, magnesium metal, aluminum metal, or hydrazine.

1 52. The method of claim 45 wherein the copper oxide
2 nanoparticles comprise Cu_2O .

1 53. The method of claim 45 wherein the copper oxide
2 nanoparticles have a diameter from about 1 nm to about 100 nm.

1 54. The method of claim 45 wherein the copper oxide
2 nanoparticles have a diameter less than about 20 nm.

1 55. The method of claim 45 wherein the copper oxide
2 nanoparticles are amorphous or crystalline.

1 56. The method of claim 45 further comprising:

2 3) heating the copper oxide-containing nanoparticles to a
3 sufficiently high temperature to form copper metal.

1 57. The method of claim 45 wherein the copper oxide
2 nanoparticles are heated to a temperature of at least 200 °C.

1 58. The method of claim 45 further comprising contacting the
2 copper oxide nanoparticles with a second reducing agent.

1 59. The method of claim 58 wherein the second reducing agent
2 is selected from the group consisting of molecular hydrogen, alcohols, amines, or
3 mixtures thereof.

ABSTRACT OF THE DISCLOSURE

The present invention provides a copper oxide-containing composition that includes copper oxide nanoparticles and one or more heteroatom donor ligands bonded to the surface of the nanoparticles, where x and y are numbers having a ratio that is equal to the ratio of the average number of M atoms to the average number of O atoms in the nanoparticles. The nanoparticles are stabilized by the one or more heteroatom donor ligands which act as a protective layer that cap the surface of the nanoparticles. The present invention also provides a solution of the copper oxide nanoparticles that may be applied to a substrate and then subsequently reduced to copper metal. Finally, the invention provides a method of preparing the copper oxide nanoparticles.




Figure 1: TEM of pyridine-protected Cu_2O nanoparticles




Figure 2: DTA/TGA of Cu_2O nanoparticles




Figure 3: TGA and its derivative curve of Cu_2O nanoparticles




Figure 4: XRD of Cu_2O nanoparticles after heating to 800°C under inert atmosphere

3/5




Figure 5: XRD of Cu₂O nanoparticles after heating to 300°C under inert atmosphere




Figure 6: XRD of Cu₂O nanoparticles after heating to 400°C under inert atmosphere

4/5




Figure 7: DTA/TGA of unbound 2,2'-bipyridyl




Figure 8: DTA/TGA of copper(II) complex of 2,2'-bipyridyl




Figure 9: DTA/TGA of bulk Cu_2O